



## Peel & Stick TPO Roofing (White)

### DESCRIPTION

GenTite Peel & Stick TPO (SA) membranes consist of a heat weldable roofing sheet laminated to a pressure sensitive adhesive. Designed for fully adhered applications, these membranes exceed all of the requirements of ASTM D 6878-03 Thermoplastic Polyolefin membrane. The membranes are reinforced with high quality polyester for added strength and stability.

### INSTALLATION

Peel & Stick TPO Membranes are designed to be installed as fully adhered systems. Refer to current GenTite Application Instructions for additional application instructions.

### PREPARATION OF SUBSTRATES

1. Substrates must be clean, dry, smooth, and free of sharp edges, tins, loose or foreign materials, oil, grease, or other materials which may damage the membrane.
2. All rough surfaces which could damage the membrane shall be repaired as specified to offer a smooth substrate.
3. All surface voids greater than 1/4" (6.35 mm) wide shall be properly filled with an acceptable material.

### INSTALLATION - MEMBRANE

1. Peel & Stick TPO is intended to be installed over dry, smooth, dust free approved substrates.
2. GenTite Primer should be applied with a medium nap roller at a coverage rate of 200 – 250 ft<sup>2</sup> per gallon (4.91-6.14 m<sup>2</sup>) one side application on concrete, masonry, and other porous and irregular substrates or on all surfaces when the temperature drops below 50°F (10°C).
3. Unroll enough GenTite Peel & Stick TPO membrane to cover the approved substrate. Position the membrane over the substrate for proper alignment and allow it to relax for 30 minutes.
4. Fold the outer half of the membrane back onto itself exposing the release liner. Remove the release liner by pulling at a 45° angle exposing the pre-applied adhesive. Roll or mate the membrane into the substrate starting in the middle of the panel working out to both edges/sides to minimize wrinkling of the panel.
5. Repeat the same procedure on the other half of the membrane. Make sure that the release liner remains in place over the seam areas.
6. Using a broom, apply positive downward pressure to the GenTite Peel & Stick membrane, working from the center out to the edges of the membrane to remove any trapped air and to increase contact points with the substrate.

GenTite™ RRS  
250 West 96<sup>th</sup> Street  
Indianapolis, IN 46260  
800-443-4272 • www.GenTite.com



## Peel & Stick TPO Roofing (White)

### INSTALLATION - SEAMS

1. Fold back the lap area without creasing the membrane and expose the bottom side of the membrane.
2. Prior to seaming the **TPO (SA)** membrane, apply GenTite Primer to the entire seam of the TPO membrane **with a Scrub Pad and Handle**. **ROLLER APPLICATION IS NOT ACCEPTABLE**. Allow the primer to dry to the touch of a clean dry finger. Remove the release liner and mate the two surfaces together with a broom or by hand pressure avoiding wrinkles and fish mouths.
3. Using a hand roller, roll the entire seam area with a silicone roller in perpendicular then parallel motions. Apply GenTite Cover Tape and Edge Caulk to all seam areas to complete the seaming process.

### PRODUCT DATA

THICKNESS	COLOR	SIZE	WIEGHT	PRODUCT #
45 mil (1.14 mm)	WHITE	6.25' x 50' (1.91 m x 15.24 m)	84 lbs (38 kg)	W59GT30068

### STORAGE

Store in original, unopened packaging and away from sources of punctures and physical damage.

Assure that structural decking will support the loads incurred by the material stored on roof top. The deck load limitations should be specified by the project designer.

### SHELF LIFE

12 months

### PRECAUTIONARY DATA

To avoid sources of punctures and physical damage, take care when moving, transporting, or handling.

Waste products such as petroleum products, greases, animal fats, and oils (mineral and vegetable) should be isolated from the membrane. Refer to Material Safety Data Sheet for additional information.

### PHYSICAL PROPERTIES

PROPERTY - MEMBRANE	ASTM TEST METHOD	MINIMUM	TYPICAL VALUES
Thickness, min, mil (mm)	D 751	39 (1.0)	45 (1.14)

GenTite™ RRS  
 250 West 96<sup>th</sup> Street  
 Indianapolis, IN 46260  
 800-443-4272 • www.GenTite.com



## Peel & Stick TPO Roofing (White)

Thickness over scrim, mil (mm) 45 (1.14)	D 6878 Annex A1	12 (0.305)	15 (0.38)
Breaking strength, min, lbf (N)	D 751	220 (976)	330 (1500)
Elongation at reinforcement break, min, %	D 751	15	30
Tearing strength, min, lbf (N)	D 751	55 (245)	156 (694)
Brittleness point, max, °F (°C)	D 2137 Method B	-40 (-40)	-49 (-45)
Ozone resistance, no cracks	D 1149	Pass	Pass
Properties after heat aging: (retained values)	D 573		
Breaking strength, % min.	D 751	90	90
Elongation at reinforcement break, % min	D 751	90	90
Tearing strength, % min.	D 751	60	60
Weight change (mass), max %	D 751	±1	-0.02
Linear dimensional change, max, %	D 1204	±1	-0.01
Water absorption, max, mass %	D 471	±3	+1.2
Factory seam strength, lbf (N)	D 751	66 (290)	75 (330)
Weather Resistance			
Visual	G 155	Pass	Pass
Breaking Strength, % min.	90	90	90
Elongation at Reinforcement Break, min, %	90	90	90
<b>PROPERTY – TAPE</b>	<b>ASTM TEST METHOD</b>	<b>MINIMUM</b>	<b>TYPICAL VALUES</b>
Color	n/a	n/a	Black
Nominal thickness – inches (mm)	E 408-71	n/a	0.008 (0.20)
Weight mil – lb/ft <sup>2</sup> (kg/m <sup>2</sup> )	n/a	n/a	0.04 (0.20)
Permeability	E 96	n/a	0.6
Specific gravity	D 71	n/a	0.93
Viscosity - cps	D 3236	n/a	30,000

GenTite™ RRS  
 250 West 96<sup>th</sup> Street  
 Indianapolis, IN 46260  
 800-443-4272 • www.GenTite.com



## Peel & Stick TPO Roofing (White)

### LEED INFORMATION

Reflectivity, % (E 903) White	74.0
Emissivity (E 408) White	0.84
Solar Reflectance Index (ASTM D 1980) White	90
Recycled Content Post Consumer Post Industrial	0% 3% - 5%
Manufacturing Location:	Tuscumbia, AL

GenTite™ RRS  
250 West 96<sup>th</sup> Street  
Indianapolis, IN 46260  
800-443-4272 • [www.GenTite.com](http://www.GenTite.com)