



Rubber Roofing (Black)

DESCRIPTION

GenTite Rubber Roofing (Black) is a non-reinforced single-ply EPDM membrane that meets or exceeds all of the requirements for ASTM D 4637-04, Type I vulcanized rubber membrane.

INSTALLATION

GenTite Rubber Roofing is intended to be installed as a fully adhered system. Refer to current GenTite Application Instructions for additional application instructions.

PREPARATION OF SUBSTRATES

Substrates must be clean, dry, smooth, and free of sharp edges, tins, loose or foreign materials, oil, grease, or other materials which may damage the membrane. All rough surfaces, which could damage the membrane, shall be repaired as specified to offer a smooth substrate. All surface voids greater than 1/4" (6.35 mm) wide shall be properly filled with an acceptable material.

PRODUCT DATA

THICKNESS	COLOR	SIZE	WIEGHT	PRODUCT #
45 mil (1.14 mm)	BLACK	10' x 25' (3 m x 7.6 m)	77 lbs (35 kg)	W59GT10165
		10' x 50' (3 m x 15.2 m)	160 lbs (73 kg)	W59GT10107
60 mil (1.52 mm)	BLACK	10' x 25' (3 m x 6.2 m)	102 lbs (46 kg)	W59GT10125
		10' x 50' (3 m x 15.2 m)	204 lbs (9 kg)	W59GT10030

STORAGE

Store in original, unopened packaging and away from sources of punctures and physical damage. Assure that structural decking will support the loads incurred by the material stored on roof top. The deck load limitations should be specified by the project designer.

SHELF LIFE

Not applicable



Rubber Roofing (Black)

PRECAUTIONARY DATA

To avoid sources of punctures and physical damage, take care when moving, transporting, or handling. Waste products such as petroleum products, greases, animal fats, and oils (mineral and vegetable) should be isolated from the membrane. Refer to Material Safety Data Sheet for additional information.

PHYSICAL PROPERTIES

PROPERTY	ASTM TEST METHOD	MINIMUM	TYPICAL VALUES
Thickness-min.inches (mm) 45 mil (1.14 mm) 60 mil (1.52 mm)	D 412	0.040 (1.02) 0.054 (1.37)	0.045 (1.14) 0.060 (1.52)
Tensile Strength – min. psi (MPa)	D 412	1305 (9.0)	1425 (9.8)
Dynamic Puncture Resistance	D 5635	Pass	Pass
Static Puncture Resistance	D 5602	Pass	Pass
Elongation, ultimate, min. - %	D 412	300	450
Tensile Set, max %	D 412	10	10
Tear Resistance – min. lbf/in (kN/m)	D 624	150 (26.27)	200 (35)
Brittleness Temperature – max °F (°C)	D 2137	-49 (-45)	-63 (-53)
Ozone Resistance – No Cracks	D 1149	Pass	Pass
Heat Aging – 240°F (116°C) 28 days			
Tensile Strength – min. psi (MPa)	D 412	1205 (8.3)	1415 (9.7)
Elongation – Ultimate min. %	D 412	200	290
Tear Resistance – min. lbf/in (kN/m)	D 624	125 (21.9)	181 (31.5)
Linear dimensional change, max, %	D 1204	±1.0	-0.7
Water Absorption – max mass % 150°F (62.6°C) 7 days	D 471	+8 (-2)	+1.8
Factory Seam Strength – min. lbf/in (kN/m)	D 816	50/sheet failure	Sheet failure
Weathering Resistance		Pass	Pass
Visual inspection PRFSE. min,%	D 518	30	30
Elongation, ultimate, min, %		200	200



Rubber Roofing (Black)

LEED INFORMATION

Reflectivity, % (ASTM C 1549)	6
Emissivity (ASTM C 1371)	0.87 (Black)
Solar Reflectance Index (ASTM D 1980)	0
Recycled Content	
Post Consumer	0%
Post Industrial	0%
Manufacturing Locations	Prescott, AR Kingstree, SC

GenTite™ RRS
250 West 96th Street
Indianapolis, IN 46260
800-443-4272 • www.GenTite.com