



DESCRIPTION

GenTite TPO Roofing (White) meets or exceeds all of the requirements for ASTM D 6878-03 Thermoplastic Polyolefin membrane. The membrane is reinforced with a 9 x 9, 1000 denier polyester scrim.

INSTALLATION

GenTite TPO is intended to be installed as a fully adhered system. Refer to current GenTite Application Instructions for additional application instructions.

PREPARATION OF SUBSTRATES

Substrates must be clean, dry, smooth, and free of sharp edges, tins, loose or foreign materials, oil, grease, or other materials which may damage the membrane. All rough surfaces which could damage the membrane shall be repaired as specified to offer a smooth substrate. All surface voids greater than 1/4" (6.35 mm) wide shall be properly filled with an acceptable material.

PRODUCT DATA

THICKNESS	COLOR	SIZE	WIEGHT	PRODUCT #
45 mil (1.14 mm)	WHITE	6.16' x 50' (1.88 m x 15.24 m)	72 lbs (33 kg)	W59GTM1407
45 mil (1.14 mm)	WHITE	10' x 25' (3.05 m x 7.63 m)	58 lbs (26 kg)	W59GTM1411

STORAGE

Store in original, unopened packaging and away from sources of punctures and physical damage. Assure that structural decking will support the loads incurred by the material stored on roof top. The deck load limitations should be specified by the project designer.

SHELF LIFE

Not applicable

PRECAUTIONARY DATA

To avoid sources of punctures and physical damage, take care when moving, transporting, or handling. Waste products such as petroleum products, greases, animal fats, and oils (mineral and vegetable) should be isolated from the membrane. Refer to Material Safety Data Sheet for additional information.



TPO Roofing (White)

PHYSICAL PROPERTIES

PROPERTY	ASTM TEST METHOD	MINIMUM	TYPICAL VALUES
Thickness, min, mil (mm)	D 751	39 (1.0)	45 (1.14) 60 (1.52)
Thickness over scrim, mil (mm) 45 (1.14) 60 (1.52)	D 6878 Annex A1	12 (0.305)	15 (0.38) 21 (0.53)
Breaking strength, min, lbf (N)	D 751	220 (976)	330 (1500)
Elongation at reinforcement break, min, %	D 751	15	30
Tearing strength, min, lbf (N)	D 751	55 (245)	156 (694)
Brittleness point, max, °F (°C)	D 2137 Method B	-40 (-40)	-49 (-45)
Ozone resistance, no cracks	D 1149	Pass	Pass
Properties after heat aging: (retained values)	D 573		
Breaking strength, % min.	D 751	90	90
Elongation at reinforcement break, % min	D 751	90	90
Tearing strength, % min.	D 751	60	60
Weight change (mass), max %	D 751	±1	-0.02
Linear dimensional change, max, %	D 1204	±1	-0.01
Water absorption, max, mass %	D 471	±3	+1.2
Factory seam strength, lbf (N)	D 751	66 (290)	75 (330)
Weather Resistance			
Visual	G 155	Pass	Pass
Breaking Strength, % min.	90	90	90
Elongation at Reinforcement Break, min, %	90	90	90
Water Vapor Permeance – Perm	E 96	n/a	0.0122
Static Puncture Resistance – lb (kg)	D 5602	n/a	33 (15)
Dynamic Puncture Resistance – J	D 5635	20	20
Puncture Resistance – lbf (N)	FTM 101C Method 2031	200 (890)	337 (1500)

GenTite™ RRS
 250 West 96th Street
 Indianapolis, IN 46260
 800-443-4272 • www.GenTite.com



TPO Roofing (White)

LEED INFORMATION

Reflectivity, % (ASTM C 1549)	77
Emissivity (ASTM C 1371)	0.87
Solar Reflectance Index (ASTM D 1980-01)	<u>Initial</u> 95 <u>Aged (3 yrs)</u> 82
Recycled Content Post Consumer Post Industrial	0% 3% - 5%
Manufacturing Location	Tuscumbia, AL

GenTite™ RRS
250 West 96th Street
Indianapolis, IN 46260
800-443-4272 • www.GenTite.com