



### DESCRIPTION

GenTite Peel & Stick Flashing (Black) is uncured EPDM membrane laminated to a cured Butyl based tape adhesive. GenTite Peel & Stick Flashing is designed to be used in Rubber Roofing (Black) applications for flashing pipes, inside corners, outside corners, and any application where uncured EPDM is required.

### INSTALLATION

Refer to current GenTite Application Instructions for additional application instructions.

1. Thoroughly mix applicable GenTite Primer. DO NOT THIN! A minimum of 2 minutes of vigorous hand mixing with a wooden paint stirrer or its equivalent is required. All sources of ignition should be eliminated; adequate ventilation should exist.
2. Clean all surfaces to receive primer with a clean cotton rag removing excess contamination prior to application of the primer.
3. With a scrub pad and handle, apply GenTite Primer using long and continuous back and forth strokes with heavy to moderate pressure along the bonding area until no streaks or puddling occurs.
4. Allow GenTite Primer to dry until slightly tacky to a dry finger touch.
5. Cut the Peel & Stick Flashing to the desired size.
6. Remove release paper from the flashing and apply it to the primed area using care not to over stretch or thin out the flashing material.
7. Using a Teflon coated or hard rubber roller, hand-roll the flashing firmly to ensure uniform contact. Pay special attention to any factory seam step downs and field seam intersections.
8. Apply a continuous "high profile" bead of GenTite Edge Caulk to the entire edge of the flashing per current specifications

### PRODUCT DATA

SIZE	QUANTITY	PRODUCT #
9" x 25' (178 mm x 8.8 m) Roll	1 Roll per Carton	W59GT10169

### STORAGE

- Store indoors in original unopened containers at a temperature between 60 °F and 80 °F (16 °C and 27 °C) for maximum shelf life.
- Do not store on roof in direct sunlight.
- When exposed to lower temperatures, restore to room temperature prior to use.

### SHELF LIFE

12 months; shelf life will be shortened if exposed to elevated temperatures.



**PRECAUTIONARY DATA**

- To avoid sources of punctures and physical damage, take care when moving, transporting, or handling.
- Refer to Safety Data Sheet (SDS) for additional information.
- GenTite Peel & Stick Flashing is semi-cured. **Do not stretch.**

**TYPICAL PROPERTIES**

EPDM	TYPICAL VALUES
Color	Black
Base	EPDM
Solids	100%
Cure State	Uncured
Thickness	.060" ± .006" (1.52 mm ± 0.152 mm)
TAPE	TYPICAL VALUES
Color	Black
Base	Butyl
Solids	100%
Cure State	Cured
Thickness	.030" ± .005" (0.635 mm ± 0.127 mm)

**LEED INFORMATION**

Recycled Content	
Post Consumer	0%
Post Industrial	0%