

# **Peel & Stick Flashing (White)**

## **DESCRIPTION**

GenTite Peel & Stick Flashing (White) is a semi-cured white EPDM flashing laminated to a cured tape. Peel & Stick Flashing is specifically designed to be used in Rubber Roofing (White) and TPO roofing applications for flashing pipes and other field fabricated flashing details.

## **INSTALLATION**

Refer to current GenTite Application Instructions for additional application instructions.

- 1. Thoroughly mix GenTite Primer. DO NOT THIN! A minimum of 2 minutes of vigorous hand mixing with a wooden paint stirrer or its equivalent is required. All sources of ignition should be eliminated; adequate ventilation should exist.
- 2. Clean all surfaces with a clean cotton rag removing excess contamination prior to application of the primer.
- 3. With a scrub pad and handle, apply GenTite Primer using long and continuous back and forth strokes with heavy to moderate pressure along the bonding area until no streaks or puddling occurs.
- 4. Allow GenTite Primer to dry until slightly tacky to a dry finger touch.
- 5. Cut the Peel & Stick Flashing to the desired size.
- 6. Peel off the release paper from the flashing, and apply it to the primed area. Use care not to overstretch or thin out the flashing material.
- 7. Using a Teflon coated or hard rubber roller, hand-roll the flashing firmly to ensure uniform contact. Pay special attention to any factory seam step downs and field seam intersections.
- 8. Apply a continuous "high profile" bead of GenTiteEdge Caulk to the entire edge of the flashing per current specifications.

#### **INSTALLATION PRECAUTIONS**

- 1. When cloudy conditions below 60 °F (15.6 °C) occur, the use of heat guns (without ignition sources) can be used to heat the flashing. This will ensure good formability of the flashing to the primer substrate.
- 2. On sunny days when the temperature is less than 70 °F (21.1 °C), place the flashing on the roof (prior to application) with the flashing side up to allow it to warm up, ensuring good formability.
- 3. On sunny days when the temperature is greater the 70 °F (21.1 °C), place the flashing on the roof (prior to application) with the release paper side up to prevent heat gain and to ensure good formability.

## **PRODUCT DATA**

SIZE	QUANTITY	PRODUCT #
12" x 25' (304 mm x 7.6 m) Roll	1 Roll per Carton	W59GT30091

GenTite™ RRS
250 West 96<sup>th</sup> Street
Indianapolis, IN 46260
800-443-4272 • www.GenTite.com



# Peel & Stick Flashing (White)

## **STORAGE**

Store indoors in original unopened containers at a temperature between 60 °F and 80 °F (16 °C and 27 °C) for maximum shelf life. Do not store on roof in direct sunlight. When exposed to lower temperatures, restore to room temperature prior to use.

## **SHELF LIFE**

12 months; shelf life will be shortened if exposed to elevated temperatures.

## **PRECAUTIONARY DATA**

To avoid sources of punctures and physical damage, take care when moving, transporting, or handling. Refer to Material Safety Data Sheet for additional information.

GenTite Peel & Stick Flashing is semi-cured. **Do not stretch.** 

## **PHYSICAL PROPERTIES**

EPDM PROPERTY	TYPICAL VALUES
Color	White
Base	EPDM
Solids	100%
Cure State	Semi-cured
Thickness	.060" (1.5 mm) ± 10%
TAPE PROPERTY	TYPICAL VALUES
Color	White
Base	Rubber Polymer
Solids	100%
Cure State	Cured
Thickness	.025" ± .007" (.635 mm ± .18 mm)

## **LEED INFORMATION**

Recycled Content	
Post Consumer	0%
Post Industrial	0%

GenTite™ RRS 250 West 96<sup>th</sup> Street Indianapolis, IN 46260 800-443-4272 • www.GenTite.com