



## Peel & Stick Flashing (White)

### DESCRIPTION

GenTite Peel & Stick Flashing (White) is a semi-cured white EPDM flashing laminated to a cured tape. Peel & Stick Flashing is specifically designed to be used in Rubber Roofing (White) and TPO roofing applications for flashing pipes and other field fabricated flashing details.

### INSTALLATION

Refer to current GenTite Application Instructions for additional application instructions.

1. Thoroughly mix GenTite Primer. DO NOT THIN! A minimum of 2 minutes of vigorous hand mixing with a wooden paint stirrer or its equivalent is required. All sources of ignition should be eliminated; adequate ventilation should exist.
2. Clean all surfaces with a clean cotton rag removing excess contamination prior to application of the primer.
3. With a scrub pad and handle, apply GenTite Primer using long and continuous back and forth strokes with heavy to moderate pressure along the bonding area until no streaks or puddling occurs.
4. Allow GenTite Primer to dry until slightly tacky to a dry finger touch.
5. Cut the Peel & Stick Flashing to the desired size.
6. Peel off the release paper from the flashing, and apply it to the primed area. Use care not to overstretch or thin out the flashing material.
7. Using a Teflon coated or hard rubber roller, hand-roll the flashing firmly to ensure uniform contact. Pay special attention to any factory seam step downs and field seam intersections.
8. Apply a continuous “high profile” bead of GenTiteEdge Caulk to the entire edge of the flashing per current specifications.

### INSTALLATION PRECAUTIONS

1. When cloudy conditions below 60 °F (15.6 °C) occur, the use of heat guns (without ignition sources) can be used to heat the flashing. This will ensure good formability of the flashing to the primer substrate.
2. On sunny days when the temperature is less than 70 °F (21.1 °C), place the flashing on the roof (prior to application) with the flashing side up to allow it to warm up, ensuring good formability.
3. On sunny days when the temperature is greater the 70 °F (21.1 °C), place the flashing on the roof (prior to application) with the release paper side up to prevent heat gain and to ensure good formability.

### PRODUCT DATA

SIZE	QUANTITY	PRODUCT #
12" x 25' (304 mm x 7.6 m) Roll	1 Roll per Carton	W59GT30091

GenTite™ RRS

800-443-4272 • www.GenTite.com



**STORAGE**

Store indoors in original unopened containers at a temperature between 60 °F and 80 °F (16 °C and 27 °C) for maximum shelf life. Do not store on roof in direct sunlight. When exposed to lower temperatures, restore to room temperature prior to use.

**SHELF LIFE**

12 months; shelf life will be shortened if exposed to elevated temperatures.

**PRECAUTIONARY DATA**

To avoid sources of punctures and physical damage, take care when moving, transporting, or handling. Refer to Material Safety Data Sheet for additional information. GenTite Peel & Stick Flashing is semi-cured. **Do not stretch.**

**PHYSICAL PROPERTIES**

EPDM PROPERTY	TYPICAL VALUES
Color	White
Base	EPDM
Solids	100%
Cure State	Semi-cured
Thickness	.060" (1.5 mm) ± 10%
TAPE PROPERTY	TYPICAL VALUES
Color	White
Base	Rubber Polymer
Solids	100%
Cure State	Cured
Thickness	.025" ± .007" (.635 mm ± .18 mm)

**LEED INFORMATION**

Recycled Content	
Post Consumer	0%
Post Industrial	0%